



MARINE SLIPWAY TROLLEY WHEEL SPECIFICATIONS



2 sizes:

- 240 mm
- 300 mm

Made to Australian standards.

Note: All wheels are supplied ready for axle drilling.





Australian Standards 1874-1988	British Standards 1400	Ingot End colour code	Cu	Sn	Pb	Zn	Al	Mn	Fe	Si	Other	Approx pouring temperature
C90710	PB1	Yellow	89.5	10							P 0.5	1000-1100°C
C90810	PB2	Yellow/Red	87.7	12							P 0.25	1070-1170°C
C93700	LB2	White	80	10	10							1000-1100°C
C94100	LB5	White/Brown	74.5	5.5	20							1000-1100°C
C92610	G1	Red	88	10	1.5	2						1000-1200°C
C83600	LG2	Blue	85	5	5	5					Ni 1	1000-1200°C
C92410	LG4	Blue/Brown	87	7	3	2						1160-1200°C
C85210	SCB1	Blue/Green	72	2	4	22						1100-1150°C
C85710	DCB3	Yellow/Brown	60		1.5	Bal	0.5					1000-1050°C
C86500	HTB1	Brown	58			37.5	1	1	1			950-1050°C
C86300	HTB3	Brown/Red	63			27	5.5	3.5	3			950-1100°C
C95210	AB1	Silver	88				9		3			1050-1150°C
C95810	AB2	Silver/Green	80				9	1	4		Ni 4.5	1100-1200°C
C95710	CMA1	Silver/Red	73				8	13	3		Ni 2	950-990°C
C87300	Si Bronz		95					1.2		4		1050-1150°C

Clingcast is a A family owned Australian full-service metal foundry offering a range of services including custom made iron products, various specialty metal base alloys and metal recycling.

Recyclable obsolete products are scrapped and sourced for our foundry and export customers.

We produce copper/alloy ingots or pour to client specific moulds and product specifications.

Our above ground mining process helps the environment through recycling what is currently in the product ecosystem and delivers quality made Australian products to our customers.